

FLEXIBLE ADHESIVE MORTAR TRASS KTF 55



- > minimises efflorescence
- > increases stability
- > flexible
- > up to 20 mm layer thickness

Product description

Powdery, water and frost-proof, highly tempered, hydraulically setting adhesive mortar for layer thickness from 3 to 20 mm especially for laying natural stone. The adhesive mortar offers more security against efflorescence and discolouration.

Indoors and outdoors for flexible laying of ceramic tiles, boards, non-translucent natural stones, mosaics, artificial stone and cotto, as well as boards with strong profiles without levelling the substrate in the course of laying.

Delivery format:

Container	Outer packaging	Pallet
25 KG / PS		48

Storage:

Can be stored frost-free, cool and dry on wooden shelves in the unopened original container for: 365 days.

Processing

Recommended tools:

Low-speed electric agitator, suitable mixing vessel, brick trowel, sponge.

The notched trowel is to be matched with the corresponding material and substrate installed.

Mixing:

Take a clean mixing vessel and add this product to water using a slow-rotating mixer until a homogeneous and lump-free blend is obtained (mixing time approx. 3 minutes).

Processing:

Apply the mortar to the substrate in two steps. In the first step a thin contact layer is scratched open, in the second step the adhesive bed is combed onto the still wet layer with the corresponding toothing at a work

41050, FLEXIBLE ADHESIVE MORTAR TRASS KTF 55, valid from: 03.06.2020, Magdalena Riegler, Page 1

Tile laying technology

angle of 45 - 60°. Rub the material to be laid into the fresh bed of mortar and remove any possible mortar residue with a wet sponge. In outdoor areas, such a swimming pools as well as areas under heavy loads, the combined laying process 'buttering floating' is to be used.
Perform an adhesion test for unknown types of stone.

Technical data

fully load-bearing	after approx. 3 - 4 days (depending on layer thickness)
Colour	grey
Can be corrected within	approx. 5 min.
Consumption	Consumption by toothing: approx. 1.8 kg/m ² at 6 mm toothing, approx. 2.4 kg/m ² at 8 mm toothing, approx. 3.1 kg/m ² at 10 mm toothing
Open time	approx. 30 min.
Rest time	none
Layer thickness	max. 20 mm
Processing time	approx. 4 hrs
Jointable/accessible	after approx. 12 - 24 hrs. (depending on layer thickness)
Water consumption	approx. 0.24 l/kg (corresponds to 6 l / 25 kg)

Test certificates

Tested in accordance with (standard, classification ...)

EN 12004

EC1 Plus

Substrate

Suitable substrates:

Suitable substrates:

Concrete

Cement screed

Anhydrite screed

Mastic asphalt

Plaster

Lime-cement plaster

Masonry

Gypsum plasterboard, Gypsum plasterboard

Smooth concrete

Aerated concrete

Wooden materials

Not suitable: on wood, metal, plastic, cement-bound substrate before final abatement of shrinkage.

The substrate must be dry, frost-free, solid, weight-bearing, dimensionally stable, free of dust, dirt, oil, grease, release agents and loose parts, and it must comply with the applicable technical national and European directives, standards and "generally accepted rules of the trade".

41050, FLEXIBLE ADHESIVE MORTAR TRASS KTF 55, valid from: 03.06.2020, Magdalena Riegler, Page 2

Product and processing instructions

Material instructions:

- When working outside the ideal temperature and/or humidity range the material properties may change significantly.
- Temper materials accordingly before processing!
- To retain the product properties, no foreign materials may be mixed in!
- Water dosing amounts or thinning specifications must be precisely kept!
- Check coloured products before use for colour consistency!
- Colour evenness can only be guaranteed within a batch.
- The colouring is significantly influenced by the environmental conditions.
- Mixed material which is already starting to stiffen may not be diluted further or mixed with fresh material!

Environmental advice:

- Do not process at temperatures below 5 °C!
- The ideal temperature range for material, substrate and air is + 15 °C to + 25 °C.
- The ideal relative air humidity range is between 40% to 60%.
- Increased humidity and/or lower temperatures delay, lower air humidity and/or higher temperatures accelerate drying, setting and hardening.
- Ensure sufficient ventilation during the drying, reaction and hardening phase; avoid draughts!
- Protect from direct sunlight, wind and weather!
- Protect adjacent components! In outdoor areas, permanently wet areas, in heavy load areas as well as for natural stone and large formats the combined process (buttering/floating) is to be used.
- Make sure children cannot access the area.
- Avoid eating, drinking and smoking while processing this product.
- Do not let it get into the sewage, drinking water or ground.

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Observe the product data sheets of all MUREXIN products used in the process.
- For heated screeds, a standard heating procedure must take place before laying.
- The underfloor heating system may not be switched on during processing and hardening.
- Clean the tools immediately after use with water.
- Wear protective gloves.
- Wear protective goggles.
- If the adhesive or the laying material comes in contact with your eyes wash immediately with plenty of water and contact an optician.
- Protect your hands with waterproof, robust gloves.
- Wear long trousers.
- Avoid longer periods of skin contact with the adhesive or laying material. Immediately and thoroughly wash affected skin with water.
- The longer fresh adhesive or installation product remains on your skin the greater the risk of serious skin damage.
- Keep children away from fresh adhesive or installation product.

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

Safety instructions

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt. This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.