

DURLIN AQUA SILK MATT PAINT SMX 50

- > water-dilutable
- > weatherproof
- > quick drying



Product description

Water-dilutable, silk-matt PU acrylic paint with excellent processing properties. Shock, scratch and impact-proof, very good flow, high degree of coverage. For indoor and outdoor matt coatings for high-quality topcoats on wood, metals, rigid PVC and mineral substrates (note substrate pre-treatment). Tintable in shade groups 1 - 4. Tintable in 171 RAL and over 40,000 other shades.

Delivery format:

Container	Outer packaging	Pallet
0,75 L / BDO	6	504
2,5 L / BDO	4	128
0,25 L / BDO	6	1.080

Storage:

Can be stored frost-free, cool and dry on wooden shelves in unopened original container: 730 days

Processing

Recommended tools:

Roller, brush, airless sprayer.
Clean the tools with water after use.

Processing:

Processing takes place by painting, rolling or spraying. Normally 1-2 work steps are required.

Technical data

Density	approx. 1.0 - 1.2 g/cm ³
Colour	White, transparent base. Can be tinted via the Murexin MIX System.
Gloss level	satin finish

53407, DURLIN AQUA SILK MATT PAINT SMX 50, valid from: 15.12.2020, Magdalena Riegler, Page 1

Colour and Coating System

Consumption	approx. 100 - 130 ml/m ² per coat
Drying time	after approx. 1 hr touch dry, after approx. 2 - 3 hrs. can be painted and sprayed over
Pigment-based	tinting carried out via lightfast coloured pigments

Substrate

Suitable substrates:

The substrate must be dry, frost-free, solid, weight-bearing, dimensionally stable, free of dust, dirt, oil, grease, release agents and loose parts, and it must comply with the applicable technical national and European directives, standards and "generally accepted rules of the trade".

Rust and loose paint residues on metallic substrates are properly removed before application.

Loose paint residues on wooden substrates are removed mechanically. Greyed and weathered wooden surfaces are pre-treated down to the weight-bearing wooden substrate.

For a perfect system

System products:

DURLIN Aqua Allgrund AV 35

Description:

DURLIN Aqua Allgrund AV 35 as quick-drying universal primer with rust protection pigments for iron, steel, galvanised surfaces, aluminium, copper, hard PVC and wood.

Product and processing instructions

Material information:

- If processing outside the ideal temperature and/or humidity range the material properties could change markedly.
- Bring the materials to the proper temperature before processing!
- In order to maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Carefully open the container, remove possible dry parts and shake the product well!
- Water-based systems have only a limited shelf life after dilution with water, which is why quick processing is recommended.
- We basically recommend carrying out an intermediate sanding between the individual applications.

Environmental information:

- The ideal temperature range for the material, substrate and air is + 15 °C to + 25 °C.
- The ideal relative humidity range is 40% to 60%.
- Increased air humidity and/or lower temperatures may prolong the drying, setting and hardening time, while lower air humidity and/or higher temperatures will speed it up.
- Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts!
- Protect against direct sunlight, wind and weather!
- Protect adjacent components!
- Do not process at temperatures below 5 °C.

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please heed the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.
- In principle, use colourless, transparent paints in UV-protected areas only.
- Observe the odours caused by solvent-based systems.
- Check material compatibility with substrates containing plasticisers.
- Watch out for dark yellowing of alkyd-based systems.
- For dimensionally stable components, observe the block resistance of the coating.

53407, DURLIN AQUA SILK MATT PAINT SMX 50, valid from: 15.12.2020, Magdalena Riegler, Page 2

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

Limiting and monitoring exposure

Personal protective equipment:

General protection and hygiene measures:

- Common safety measures for handling chemicals are to be observed.
- Keep away from foodstuffs, beverages and feedstuffs.
- Take off contaminated, impregnated clothing immediately.
- Wash your hands before taking breaks and when finishing work.

Breathing protection: not required.

Hand protection: Not required.

Glove material

- The selection of a suitable glove depends not only on the material, but also on other quality properties, which may vary from manufacturer to manufacturer.

Penetration time of the glove material

- The precise penetration time is to be found out from the protective glove manufacturer and complied with.

Eye protection: Protective goggles recommended when decanting.

Body protection: Protective clothing.

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt. This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.