

PARQUET ADHESIVE X-BOND MS-K 530



- > shear-resistant adhesive according to DIN 281
- > water and solvent-free
- > suitable for all common types of wood and parquet

Product description

High-quality, single-component, shear-resistant, water and solvent-free parquet adhesive based on MSP technology. Has no migration-capable components. Suitable for all substrates and for all types of parquet. For gluing strip parquet in accordance with DIN EN 13226, edgewise in accordance with DIN EN 14761, mosaic parquet in accordance with DIN EN 13488, lam parquet in accordance with DIN EN 13489, solid boards, double- and triple-layer parquet, and table parquet. Suitable for underfloor heating systems.

Delivery format:

| Container | Outer packaging | Pallet |
|------------|-----------------|--------|
| 16 KG / KE | | 33 |

Storage:

Can be stored frost-free, cool and dry on wooden shelves in the unopened original container for: 365 days

Processing

Recommended tools:

Notched trowel B3, B5, PK/B11, B15, B17

Processing:

The adhesive must be applied to the whole surface of the substrate with a suitable notched trowel. Working time is approx. 30 - 45 minutes. The parquet must be laid in the adhesive bed with gentle sliding motions and pressed down firmly, so the rear side of the parquet is fully covered with the adhesive. Walkable after approx. 12 hours. The laid parquet floor can be sanded for the first time after 36 hours at the earliest. The wood moisture must meet the relevant ÖNORM standards for adhesion. Observe the parquet manufacturer's laying guidelines. Remove adhesive contaminants in the freshly laid state with R 500 cleaning cloths. Once set, the adhesive can only be removed mechanically.

Technical data

| | |
|------------------------|--|
| Working time | approx. 30 - 35 min. |
| Final strength | after approx. 48 hrs |
| Consumption | Consumption depending on substrate, parquet type and tothing: approx. 0.8 - 1.2 kg/m ³ , Tothing B3, B5, PK/B11, B15: ca. 0,7 - 1,5 kg/m ² , Tothing B17: approx. 1.8 kg/m ² |
| Processing temperature | Ideally: +16 °C to +25 °C |
| Specific weight | 1,6 g/cm ³ |

Test certificates

Tested in accordance with (standard, classification ...)

GEV Emicode EC1 Plus
DIBT-Zulassung Z-155.10-100
EN 14293
DIN 281

Substrate

Suitable substrates:

Standard mineral substrates
Cement screeds and concrete floors
Calcium sulphate screeds
Mastic asphalt
Wooden substrates
Dry screed
coated substrates

The substrate must be dry, free of frost, solid, load-bearing, dimensionally stable and free of dust, dirt, oil, grease, solvents and loose parts and correspond to the applicable technical national and European guidelines, standards as well as meet the "generally accepted rules of the trade".

With proper substrates the priming coat can be omitted. Substrates are to be carefully sanded and vacuumed well. Do not prime before adhesion on smoothed surfaces. If priming is required to remove dust or to achieve readiness for installation, use Penetrating Primer D7, Primer PU 5 Express, Epoxy Resin Coating EP 170, Silane Primer MS-X 3 or Special Adhesive Primer DX 9.

Product and processing instructions

Material advice:

- When working outside the ideal temperature and/or humidity range, the material properties may change significantly.
- Temper materials accordingly before processing!
- To retain the product properties, no foreign materials may be mixed in!
- Water dosing amounts or thinning specifications must be precisely kept!

66016, PARQUET ADHESIVE X-BOND MS-K 530, valid from: 29.06.2020, Magdalena Riegler, Page 2

Parquet and adhesion technology

- Check coloured products before use for colour accuracy!
- Colour consistency can only be guaranteed within a batch.
- The colouring is significantly influenced by the environmental conditions.
- The adhesive contents may cause damaging interactions with the surface treatment materials.

Environmental advice:

- DO not process at substrate temperatures under +15°C!
- The ideal temperature range for material, substrate and air is +15 °C to +25 °C.
- The ideal relative air humidity range is between 40% to 60%.
- Increased humidity and/or lower temperatures delay, lower air humidity and/or higher temperatures accelerate drying, setting and hardening.
- Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts! - Protect from direct sunlight, wind and weather!
- Protect adjoining components!

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Observe the product data sheets of all MUREXIN products used in the system.
- Keep a genuine original container of the respective batch for later repair work.

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt. This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.