

PROFI TERRACE OIL TP 92

- > quick drying
- > hard-wearing surface
- > UV-protection
- > mould- and fungus-resistant



Product description

High-quality, water-based impregnating oil for outdoors. For basic care and maintenance of new or wooden surfaces previously treated with oil. (e.g., terraces, garden furniture, wooden facades). The Profi Terrace Oil TP 92 achieves a water and dirt-proof surface and protects the wood from mould.

Delivery format:

Container	Outer packaging	Pallet
2,5 L / BLE	4	168

Storage:

Can be stored for about 36 months in a frost-free, cool, and dry environment on a wooden rack in the unopened original container.

Processing

Recommended tools:

Brush, lint-free cotton cloth, short brush painter roller

Mixing:

The contents of the container must be stirred thoroughly before using Murexin Profi Terrace Oil TP 92.

Processing:

Use a suitable tool to apply a thin and even layer of Profi Terrace Oil TP 92. The terrace oil can appear white when wet. The excess oil should be removed after a maximum of 5 minutes with a lint-free and clean cotton cloth. The wood can be repolished with a polishing pad or polishing machine as soon as it is dry. This makes the surface even more durable. It may take up to 48 hours until the oil has completely hardened.

Technical data

Consumption

| 8 - 12 m²/l - depending on the wood type

Substrate

Suitable substrates:

all untreated or oiled wooden surfaces.

The substrate must be free of dust, dirt, oil, grease, silicon, separating agents, washing residues. The requirements of the applicable standards, guidelines, and data sheets apply.

Suitable substrate pre-treatment:

The substrate must be free of dust, dirt, oil, grease, silicon, separating agents, washing residues. The requirements of the applicable standards, guidelines, and data sheets apply.

Product and processing instructions

Material information:

- The properties of the material may be significantly altered if not processed within the ideal temperature and/or humidity range.
- Bring the materials to the proper temperature before processing!
- To maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Check tinted products for colour accuracy before application!
- Colour consistency can only be guaranteed within the same batch.
- The environmental conditions significantly impact colour formation.

Environmental information:

- Do not process at substrate temperatures below +15°C!
- The ideal temperature range for the material, substrate, and air is +15°C to +25°C.
- The ideal humidity range is 40% to 60% relative humidity.
- Increased air humidity and/or lower temperatures may prolong the drying, setting, and hardening time, while lower air humidity and/or higher temperatures will speed it up.
- Ensure adequate ventilation during the drying, reaction, and hardening phase; avoid draughts!
- Protect against direct sunlight, wind, and weather!
- Protect adjacent components!

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please observe the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.

The information provided reflects average values obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted. Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt. This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.